

# FT2

## Adhesive tape



Tel: +44 (0) 1274 550500  
Fax: +44 (0) 1274 550501  
Email: [sales@aerovac.com](mailto:sales@aerovac.com)  
Website: [www.aerovac.com](http://www.aerovac.com)

- Polyester tape, backed with a fully cured, pressure sensitive adhesive.
- Excellent temperature and pressure resistance.
- Strips easily after use.

#### PHYSICAL PROPERTIES

- |                            |                                   |
|----------------------------|-----------------------------------|
| • Maximum cure temperature | 180°C (acrylic), 204°C (silicone) |
| • Colour                   | Turquoise                         |
| • Adhesive                 | Acrylic, silicone                 |
| • Carrier                  | Polyester                         |
| • Total thickness          | 75µ                               |
| • Adhesive thickness       | 50µ                               |
| • Tape thickness           | 25µ                               |
| • Elongation at break      | 100%                              |

#### AVAILABILITY & PACKAGING

- |                   |                           |
|-------------------|---------------------------|
| • Standard widths | 12.5mm, 25mm, 50mm, 100mm |
| • Standard length | 66m                       |

#### STORAGE & HANDLING

- Handling of these products must conform to individual company guidelines and health and safety regulations.

Aerovac Systems Ltd <a href="http://www.aerovac.com">www.aerovac.com</a>	Aerovac Systems Italy S.r.l. <a href="http://www.aerovac.it">www.aerovac.it</a>	Aerovac Systèmes France <a href="http://www.aerovac.fr">www.aerovac.fr</a>	Richmond Aircraft Products <a href="http://www.richmondaircraft.com">www.richmondaircraft.com</a>
---	--	---	--

Aerovac Systems Ltd.

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith. All values stated are nominal. For further details about tolerances please contact Aerovac Systems quality department.

Revised: February 2010