

# D300 Peel ply



Tel: +44 (0) 1274 550500  
Fax: +44 (0) 1274 550501  
Email: [sales@aerovac.com](mailto:sales@aerovac.com)  
Website: [www.aerovac.com](http://www.aerovac.com)

- A porous, medium weight nylon 6.6 peel ply.
- Heat set and scoured, for use directly against laminates or bond lines.
- Not coated with any release solution and as such will not contaminate the composite part.
- Coloured pink for ease of detection and removal from the cured laminate.
- Aerovac does not recommend the use of woven nylon fabrics with phenolic resin or pre-preg systems as acid in the catalyst can break down nylon materials. Therefore we recommend the customer conduct their own internal compatibility tests.
- Aerovac does not recommend the use of woven nylon fabrics at temperatures exceeding 180°C. Over this temperature, it is suggested that our coated nylon release fabrics (A8888 and B4444) or porous PTFE release fabric (FF03PM) be used.

## PHYSICAL PROPERTIES

- Maximum cure temperature 180°C
- Colour Pink
- Fabric type Nylon
- Fabric weight 92g/m<sup>2</sup>

## AVAILABILITY & PACKAGING

- Standard width 1.52m
- Standard length 100m
- Slit widths available

## STORAGE & HANDLING

- No special storage conditions required.
- Handling of these products must conform to individual company guidelines and health and safety regulations.

Aerovac Systems Ltd <a href="http://www.aerovac.com">www.aerovac.com</a>	Aerovac Systems Italy S.r.l <a href="http://www.aerovac.it">www.aerovac.it</a>	Aerovac Systèmes France <a href="http://www.aerovac.fr">www.aerovac.fr</a>	Richmond Aircraft Products <a href="http://www.richmondaircraft.com">www.richmondaircraft.com</a>
---	---	---	--

Aerovac Systems Ltd.

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith. All values stated are nominal. For further details about tolerances please contact Aerovac Systems quality department.

Revised: February 2010