

# POLY 1

## Adhesive tape



Tel: +44 (0) 1274 550500  
Fax: +44 (0) 1274 550501  
Email: [sales@aerovac.com](mailto:sales@aerovac.com)  
Website: [www.aerovac.com](http://www.aerovac.com)

- High temperature polyimide tape.
- Used to hold down the consumable package on high temperature cure work.
- Can also be used to hold down the edge of the bagging membrane to the tool surface, as most high temperature sealant tapes do not exhibit much tack at room temperature.

#### PHYSICAL PROPERTIES

- |                            |          |
|----------------------------|----------|
| • Maximum cure temperature | 260°C    |
| • Colour                   | Amber    |
| • Adhesive                 | Silicone |
| • Carrier                  | Nylon    |
| • Total thickness          | 65µ      |
| • Adhesive thickness       | 40µ      |
| • Tape thickness           | 25µ      |
| • Elongation at break      | 63%      |

#### AVAILABILITY & PACKAGING

- |                   |                    |
|-------------------|--------------------|
| • Standard widths | 12.5mm, 25mm, 50mm |
| • Standard length | 33m                |

#### STORAGE & HANDLING

- Handling of these products must conform to individual company guidelines and health and safety regulations.

Aerovac Systems Ltd <a href="http://www.aerovac.com">www.aerovac.com</a>	Aerovac Systems Italy S.r.l <a href="http://www.aerovac.it">www.aerovac.it</a>	Aerovac Systèmes France <a href="http://www.aerovac.fr">www.aerovac.fr</a>	Richmond Aircraft Products <a href="http://www.richmondaircraft.com">www.richmondaircraft.com</a>
---	---	---	--

Aerovac Systems Ltd.

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith. All values stated are nominal. For further details about tolerances please contact Aerovac Systems quality department.

Revised: February 2010