

# Airbleed 100/Airbleed 100 Grey Polyester Breather/Bleeder Fabric

- Medium weight polyester breather fabric with excellent all round stretch and drapeability
- Effective for use in conjunction with components containing complex curvatures or acute radii
- Felted construction facilitates efficient resin bleed without risk of bridging, and use in single or multiple layers

## PHYSICAL PROPERTIES

- Viscat softening point 80°C
- Maximum Cure Temperature 205°C
- Fibre 100% Polyester
- Colour White or Grey
- Weight (nominal) 150g/m<sup>2</sup>
- Thickness 3.4mm (nominal, uncompressed)

Note: Airbleed 100 has no release characteristics and should be separated from the laminate by a suitable porous release fabric or film. Airbleed 100 is not intended to be used as a breather material alone in high pressure autoclave cures.

## AVAILABILITY & PACKAGING

- Standard roll sizes 100m x 0.76m and 1.52m wide up to 3m wide available to order
- Cut shapes/Slit widths Available to order
- Packaging Heavy gauge polyethylene Wound on 76mm diameter cores

## STORAGE & HANDLING

- No special storage conditions required
- No skin irritation problems experienced

## Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: [sales@aerovac.com](mailto:sales@aerovac.com) website: [www.aerovac.com](http://www.aerovac.com)

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.