

Airbleed 40N

100% Nylon breather fabric

- Heavy weight 100% nylon 66 needled fabric
- Developed for high temperature and high pressure autoclave cures, offering improved air flow characteristics
- Extremely resistant to 'locking off' under pressure

PHYSICAL PROPERTIES

| | |
|----------------------------|-----------------------------|
| • Viscat Softening Point | Approx 245°C |
| • Maximum Cure Temperature | 232°C |
| • Material | 100% Nylon 66 |
| • Weight | 400 g/m ² |
| • Thickness | 6mm (nominal, uncompressed) |
| • Melt point | 252°C |

Note: Airbleed 40N has no release characteristics and therefore must be separated from the laminate by a suitable release fabric or film

AVAILABILITY & PACKAGING

- Standard rolls 50m x 1.52m wide
- Wide widths, up to 6 metres wide, available upon request

STORAGE & HANDLING

- No special storage conditions required
- No skin irritation problems encountered

Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: sales@aerovac.com website: www.aerovac.com

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.

revision: N/A new