

AS Silicone Rubber

- Extremely strong with high elasticity and tear resistance
- Ideal for use as a vacuum membrane, when curing advanced composites at high temperatures and pressures
- No post cure is required, as the material becomes stable during its first cure

PHYSICAL PROPERTIES

	Grey	Translucent
• Hardness (Shore A)	44	62
• Tensile Strength	26daN/cm (mini)	30daN/cm (mini)
• Density	1.14	1.20
• Max Temp	250°C	250°C
• Elongation	593%	450%

AVAILABILITY & PACKAGING

- Thickness Up to 3mm
- Width 1.3m

STORAGE & HANDLING

- No risk of allergic reaction
- Store below 180°C for max of 1 year
- Does not vulcanise once stored cold
- Store in original packaging. Do not contaminate

Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: sales@aerovac.com website: www.aerovac.com

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.