

# A6000

## Fluoropolymer Release Film

- High temperature, tough, fluoropolymer EFTE release film exhibiting excellent release characteristics, combined with high elongation
- Suitable for use with all commonly used resin systems
- Opaque blue for ease of identification on the cured laminate

### PHYSICAL PROPERTIES

- Maximum Use Temperature Up to 260°C
- Colour Blue
- Tensile strength at break (7000 psi)/48 Mpa
- Elongation at Break >350%
- Density 1.75g/cm<sup>3</sup>
- Melt Point 275-285°C

### AVAILABILITY & PACKAGING

- Thickness 0.012mm, 0.015mm and 0.020mm
- Yield 47.5 m<sup>2</sup>/Kg (0.012mm thick)  
38.0 m<sup>2</sup>/Kg (0.015mm thick)  
28.5 m<sup>2</sup>/Kg (0.020mm thick)
- Roll size 150m x 1.30m wide
- Available in a range of perforations

### STORAGE & HANDLING

- Store in original packaging
- No handling problems experienced

## Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: [sales@aerovac.com](mailto:sales@aerovac.com) website: [www.aerovac.com](http://www.aerovac.com)

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.

revision: May 2002