

VACFILM 300R

- Developed for direct contact use with prepreg during fabrication of hollow structures such as masts, bicycle components, aircraft ducting etc.
- Material withstands high pressures and self releases from epoxy and phenolic prepreps
- Available in a wide range of sizes from 50mm up to 1500mm layflat tube

PHYSICAL PROPERTIES

- Maximum Use Temperature 160°C
- Thickness 0.070mm
- Tensile strength (ASTM D882) 50 ± 10%
- Elongation at break (ASTM D882) 300 ± 10%
- Colour Red

AVAILABILITY & PACKAGING

- Widths a number of widths are available from stock

HANDLING & SAFETY

- VACFILM300R is a hydrophilic material. Moisture and water act as plasticizers. The level of moisture content at time of use is therefore an important criteria for successful performance.

Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: sales@aerovac.com website: www.aerovac.com

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.

revision: N/A new