

# Vacfilm 430 High Stretch Elastomeric Bagging Film

- A tough high elongation elastomeric bagging film, suitable for de-bulking applications and oven curing of composites up to a temperature of 120°C
- Reduction in pleats during application due to high elasticity of the film
- Good release from sealant tape
- Excellent recovery after elongation enables the film to be reused on subsequent de-bulking operations

## PHYSICAL PROPERTIES

- Maximum Use Temperature 120°C (Oven air temperature must not exceed 130°C)
- Colour Transparent
- Tensile Strength (ultimate) 4000 psi ASTM D-412
- Elongation (ultimate) 430%
- Tensile Modulus 700 psi at 100% elongation  
ASTM D-142
- Tear Resistance 650 PPI
- Melt Point 145°C

## AVAILABILITY & PACKAGING

- Thickness 0.050mm
- Roll Length 250m (Smaller quantities available)
- Roll Width 2.05m
- Yield 16.8 m<sup>2</sup>/Kg

## STORAGE & HANDLING

- No special requirements

## Aerovac Systems Ltd.

Tel: 01274 550500 Fax: 01274 550501 e-mail: [sales@aerovac.com](mailto:sales@aerovac.com) website: [www.aerovac.com](http://www.aerovac.com)

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith.